DATA SHEET

G-6

Ceramic Core Material

© 2015 Certech, Inc., a business within Morgan Advanced Materials			
Description		Physical Properties	
General core type with an intermediate particle size distribution for Equiax castings. Formulated to be used for large land-based type cores that require good stability at elevated temperatures and for chunky airfoil cores up to 30 inches long. Contains fugitive filler to enhance the permeability of the core body. Used in applications where there is a probability of gas reactions.		Modulus of rupture (4-point), psi	1350
		Length shrinkage (mold-to-fired), %	0.4
		Chord shrinkage (mold-to-fired), %	0.6
		Thermal expansion coefficient (25 - 1000°C), ppm/°C	1.8
Major Chemistry		Bulk density, g/cc	1.8
Silica (SiO ₂), %	70	Apparent density, g/cc	2.6
Zircon (ZrSiO ₄), %	30	Porosity, %	30
Trace Element Analysis		Absorption, %	17
Iron (Fe), ppm	< 900	Cristobalite content (after fire), %	4
Bismuth (Bi), ppm	< 1	Cristobalite content (after 15 min. at 1390°C), %	6
Lead (Pb), ppm	< 25		· ·
Silver (Ag), ppm	< 25	Leachability (30% boiling KOH, 30 g sample, 30 min.), %	100
Antimony (Sb), ppm	< 25		
Tin (Sn), ppm	< 25	Core – Metal Reaction Compatibility	
Zinc (Zn), ppm	< 50	Most nickel based, DS and SX alloys.	

Please note that all values quoted are based on test pieces and may vary according to component design. These values are not guaranteed in anyway whatsoever and should only be treated as indicative and for guidance only. Aug.12.2015