

Data Sheet

Gold - ABA[®]

Description:

High-purity Active Braze Alloy of gold, nickel and titanium, developed for direct application to ceramic surfaces.

Nominal composition by weight: **96.4% Au, 3.0% Ni and 0.6% Ti**

Prime features:

- Wets and bonds to virtually any metallic surface, as well as to non-metallics such as oxides, nitrides and carbides
- Allows ceramic-to-ceramic and ceramic-to-metal surfaces to be brazed without metallizing, firing and electroplating
- Cuts time and costs in manufacture of ceramic/metal assemblies
- Produces strong, highly reliable and vacuum-tight brazed joints

Typical applications:

- Aerospace components
- Medical equipment components
- Vacuum tubes
- Wave guide and Klystron assemblies

Physical Properties*

Liquidus Temperature	1030 °C
	1886 °F
Solidus Temperature	1003 °C
	1837 °F
Coefficient of Thermal Expansion (CTE)	16.1 x 10 ⁻⁶ /C, for 20 – 850 °C
	8.94 x 10 ⁻⁶ /°F, for 68 – 1562 °F
Thermal Conductivity (Calculated)	25.0 W/m·K
	14.4 BTU/ft·h· °F
Density	18.3 Mg/m ³
	0.661 lb/in ³
Yield Strength (0.2% offset)	209 MPa
	30.3 x 10 ³ lb/in ²
Tensile Strength	334 MPa
	48.5 x 10 ³ lb/in ²
Elongation (2in/50mm gage section)	29%
Electrical Resistivity	308 x 10 ⁻⁹ ohm·m
Electrical Conductivity	3.25 x 10 ⁶ /ohm·m
Vapor Pressure (Calculated)	
Recommended Brazing Temperatures	1025 – 1030 °C
Recommended Brazing Atmospheres	10 ⁻⁵ mm Hg

* Please note that all values quoted are based on test pieces and may vary according to component design. These values are not guaranteed in any way and should only be treated as indicative values. They should be used for guidance only and for no other purpose whatsoever.

Impurity Limits

Zn	less than 0.001%
Cd	less than 0.001%
Pb	less than 0.002%
P	less than 0.002%
C	less than 0.01%

All other metallic impurities having a vapor pressure higher than 10⁻⁷ mm Hg at 500 °C are limited to 0.002% each. Impurities having a vapor pressure lower than 10⁻⁷ mm Hg at 500 °C are limited to a total of 0.075%. (This applies to all forms except powder and extrudable paste.)

Supplied as:

- Wire
- Foil

The determination as to the adaptability of any Wesgo materials to the specific needs of the Buyer is solely the Buyer's prerogative and responsibility. All technical information, data and recommendations are based on tests and accumulated experience data, which Wesgo believed to be reliable. However, the accuracy and completeness thereof are not guaranteed.