Data Sheet

Palniro® 4 (AMS 4785)

Description:

High-purity gold, nickel and palladium alloy for vacuum brazing. Nominal composition by weight: 30% Au, 36% Ni and 34% Pd

Prime features:

- High ductility
- High strength
- High oxidation resistance
- Recommended for brazing super alloys and stainless steels
- Similar to Palniro 4 but lower brazing temperature

Typical applications:

- Aero-engines (OEM and repair)
- Aerospace fuel-line assemblies
- Vacuum tubes
- Wave guide and Klystron assemblies
- Power supply surge arrestors

Physical Properties*

| Liquidus Temperature | 1169 ℃ |
|--|---|
| | 2139 °F |
| Solidus Temperature | 1135 °C |
| | 2075 °F |
| Coefficient of Thermal Expansion (CTE) | 17.0 x 10 ⁻⁶ /C, for 20 – 1000 °C |
| | 9.6 x 10 ⁻⁶ /°F, for 68 – 1832 °F |
| Thermal Conductivity (Calculated) | |
| | |
| Density | II.6 Mg/m³ |
| | 0.419 lb/in ³ |
| Yield Strength (0.2% offset) | 655 MPa |
| | 95 x 10 ³ lb/in ² |
| Tensile Strength | 829 MPa |
| | 120 x 10 ³ lb/in ² |
| Elongation (2in/50mm gage section) | 28% |
| Electrical Resistivity | 162 x 10 ⁻⁹ ohm·m |
| Electrical Conductivity | XXX x 10 ⁶ /ohm·m |
| Vapor Pressure (Calculated) | 2 x 10 ⁻⁶ mm Hg @ 1000 °C, 1832 °F |
| | 2 x 10 ⁻⁵ mm Hg @ 1100 °C, 2012 °F |
| Recommended Brazing Temperatures | |
| Recommended Brazing Atmospheres | 10 ⁻⁵ mm Hg, inert gas |

^{*} Please note that all values quoted are based on test pieces and may vary according to component design. These values are not guaranteed in any way and should only be treated as indicative values. They should be used for guidance only and for no other purpose whatsoever.

Impurity Limits

| Zn | less than 0.001% |
|----|------------------|
| Cd | less than 0.001% |
| Pb | less than 0.002% |
| Р | less than 0.002% |
| С | less than 0.01% |

All other metallic impurities having a vapor pressure higher than 10^7 mm Hg at $500\,^{\circ}\text{C}$ are limited to 0.002% each. Impurities having a vapor pressure lower than 10^7 mm Hg at $500\,^{\circ}\text{C}$ are limited to a total of 0.075%. (This applies to all forms except powder and extrudable paste.)

Supplied as:

- Foil
- Flexibraze
- Wire
- Powder
- Extrudable paste
- Preforms

The determination as to the adaptability of any Wesgo materials to the specific needs of the Buyer is solely the Buyer's prerogative and responsibility. All technical information, data and recommendations are based on tests and accumulated experience data, which Wesgo believed to be reliable. However, the accuracy and completeness thereof are not guaranteed.